





# METHOD FOR COATING METALLIC SURFACES AND USE OF THE SUBSTRATES COATED IN THIS MANNER






**Patent number:** WO02070782  
**Publication date:** 2002-09-12  
**Inventor:** KOLBERG THOMAS (DE); RENGNET-FERRIER SEVERINE (CA); BITTNER KLAUS (DE); WENDEL THOMAS (DE); WIETZORECK HARDY (DE); SCHUELLELMANN GERRIT (DE); SPECHT JUERGEN (DE)  
**Applicant:** CHEMETALL GMBH (DE); KOLBERG THOMAS (DE); RENGNET-FERRIER SEVERINE (CA); BITTNER KLAUS (DE); WENDEL THOMAS (DE); WIETZORECK HARDY (DE); SCHUELLELMANN GERRIT (DE); SPECHT JUERGEN (DE)  
**Classification:**  
- international: **C23C22/18; C23C22/36; C23C22/73; C23C22/05; C23C22/73; (IPC1-7): C23C22/18; C23C22/36**  
- european: **C23C22/18E; C23C22/36D; C23C22/73**  
**Application number:** WO2002EP02290 20020301  
**Priority number(s):** DE20011010834 20010306

## Also published as:

 WO02070782 (A3)  
 EP1390564 (A3)  
 EP1390564 (A2)  
 US2004129346 (A1)  
 DE10110834 (A1)

more >>

## Cited documents:

 DE4013483  
 DE19500562  
 WO9322474  
 DE4210513  
 EP0564287

more >>

[Report a data error here](#)

## Abstract of WO02070782

The invention relates to a method for coating metallic surfaces by a manganese-zinc phosphatizing process, using an aqueous phosphatizing solution, in which nickel is deliberately not added. Said method is characterized in that the zinc: manganese weight ratio of the phosphatizing solution is maintained in the region of between 0.05: 1 and 0.99: 1 and that the phosphatizing solution has the following contents: between 0.05 and 5 g/l zinc, between 0.075 and 5.2 g/l manganese and between 0.008 and 0.050 g/l copper and/or hexafluoride complexes of titanium, hafnium and/or zirconium totalling between 0.002 and 0.5 g/l, calculated as F6. The invention also relates to the use of the metal parts coated in this manner.

---

Data supplied from the **esp@cenet** database - Worldwide